


**bonding recommendation:**

**WULFF GmbH u. Co. KG**  
 Postfach 12 61 • 49499 Lotte  
 Wersener Str. 3 • 49504 Lotte  
 Telefon 0 54 04 / 8 81-0  
 Telefax 0 54 04 / 8 81-819  
 E-mail: info@wulff-gmbh.de  
 www.wulff-gmbh.de

**Banken:**  
 Commerzbank Osnabrück  
 IBAN: DE71 2654 0070 0533 5518 00 | BIC: COBADEFFXXX  
 Kreissparkasse Steinfurt  
 IBAN: DE13 4035 1060 0025 0002 09 | BIC: WELADED1STF  
 Postbank Hannover  
 IBAN: DE72 2501 0030 0078 8953 03 | BIC: PBNKDEFFXXX

|  |   |   |   |  |   |
|--|---|---|---|--|---|
| <b>PVC-design flooring (LVT)</b>                     |   | <b>PROJECT FLOORS GmbH</b><br><b>Max-Ernst-Straße 4</b><br><b>D-50354 Hürth</b><br><b>Telefon +49 (0) 2233 9687-0</b><br><b>Fax +49 (0) 2233 9687-10</b><br><b>www.project-floors.com</b><br><b>info@project-floors.com</b> |   |  |   |
| <b>Adhesive</b>                                      | WULFF Supra-Strong●<br>fibre-reinforced premium wet adhesive 1)                               |   |   | Tooling TKB A2   | <br><a href="http://www.blauer-engel.de/uz113">www.blauer-engel.de/uz113</a><br><b>„The blue Engel“<br/>to RAL-UZ 113</b> |
|  | WULFF Multi-Strong●<br>fibre-reinforced multi-purpose wet adhesive 1)                         |   |   | Tooling TKB A2   |   |
|  | WULFF Ultra-Strong●<br>fibre-reinforced premium wet adhesive 1)                               |   |   | Tooling TBK A2   |   |
| <b>Leveling-Compound, Layer thickness mind. 2 mm</b> | SA 60 PLUS●<br>SA 50 PLUS●<br>2K AM 10●<br>DS 80●<br>SA 25●<br>Floor- Direkt●<br>GP 200 PLUS● | SA 60 PLUS●<br>SA 50 PLUS●<br>2K AM 10●<br>DS 80●<br>SA 25●<br>Floor- Direkt●<br>GP 200 PLUS●   | max. 3 mm:<br>2K AM 10●<br>SA 60 PLUS●<br>SA 50 PLUS●<br>SA 25●<br>Floor- Direkt●<br>max. 10 mm<br>GP 200 PLUS● | 2K AM 10●  | SA 60 PLUS●<br>SA 50 PLUS●<br>2K AM 10●<br>DS 80●<br>SA 25●<br>Floor- Direkt●<br>GP 200 PLUS●   |
|  | <b>Primer</b>   | Micro-Grund●<br>Unigrund Express●<br>NDV 1●<br>Super Grip Q●  | Micro-Grund●<br>Unigrund Express●<br>Super Grip Q●  | 2K DP-Grund 3)●<br>Unigrund Express●<br>EP-BA 583 (gritted)<br>Super Grip Q● | 2K DP-Grund 3)●<br>Unigrund Express●<br>EP-BA 583 (gritted)<br>Super Grip Q●  |
| <b>Underground processing<sup>2)</sup></b>           | grind, vacuum   | grind, vacuum   | grind, vacuum   | grind, vacuum  | grind, vacuum   |
| <b>Substrates</b>                                    | Cement screeds  | Calcium sulphat screeds   | Mastic asphalt (IC 10, DIN EN 13813) not gritted  | Wood planks, chipboard and OSB (to DIN 68771)                                | Sound and waterproof adhesive residue (Self-tests)  |
| <b>Residual moisture</b>                             | < 2,0 CM% non-heated<br>< 1,8 CM% heated  | < 0,5 CM% non-heated<br>< 0,3 CM% heated  | Not applicable  | Not applicable   | Not applicable  |

- 1) Dispersion adhesives are not permanently resistant to moisture; if necessary, the lining seams must be sealed / welded.  
 2) The BEB and TKB information sheets for the assessment and preparation of subsoils must be observed. Substrates must be dry, load-bearing, clean and crack-free according to DIN 18365.  
 3) Must not be filled with calcium sulfate fillers GP 200 PLUS (Stand 12/2021)